



tesa® 6701 New Bond



Product Information

640µm double-sided acrylic foam tape

Product Description

tesa® 6701 is acrylic foam tape in white color, the AC foam works both as backing and adhesive.

Product features:

- Good bonding on metal and plastic substrates
- Good shear resistant
- Good temperature resistant

Product Features

- Sufficient bonding on different substrates
- Good shear resistant
- Temperature resistant

Application Fields

Example mounting applications include but are not limited to:

- Decoration glass and panel mounting
- Part and logo mounting
- Control panel mounting
- Stiffener mounting

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-----------------|-------------------|--------|
| • Backing | foamed acrylic | • Total thickness | 640 µm |
| • Type of adhesive | pure acrylic | • Color | white |
| • Type of liner | PE-coated paper | | |

Properties/Performance Values

- | | | | |
|-----------------------------------|--------------|-------------------------------------|-----------|
| • Elongation at break | 850 % | • Static shear resistance at 70°C | very good |
| • Tensile strength | 3.9 N/cm | • Temperature resistance long term | 100 °C |
| • Static shear resistance | good, medium | • Temperature resistance short term | 200 °C |
| • Static shear resistance at 23°C | very good | | |

For latest information on this product please visit <http://l.tesa.com/?ip=06701>



tesa[®] 6701 New Bond

Product Information

Adhesion to Values

• ABS (initial)	10 N/cm	• PC (initial)	14 N/cm
• ABS (after 3 days)	13 N/cm	• PC (after 3 days)	16 N/cm
• Aluminium (initial)	16 N/cm	• PMMA (initial)	13 N/cm
• Aluminium (after 3 days)	26 N/cm	• PMMA (after 3 days)	16 N/cm
• Glass (initial)	16 N/cm	• Steel (initial)	16 N/cm
• Glass (after 3 days)	20 N/cm	• Steel (after 3 days)	25 N/cm

Additional Information

Liner variants:

PV01 White paper with blue logo, d/s release coating (150µm)

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=06701>